

Report of Analysis

Client: Pathfinders Lubricants
37 Harrison Ave.
Aurora, Ontario
L4G 1E2
Canada


Lab Report no.: **CA120-6840-2**
Report date: December 21, 2009

From: Pathfinders Lubricants, Aurora
Submitted on: December 14, 2009
Tested on: December 15, 2009
Customer Product
Description: Diesel
Sample identification: Diesel

Attention: Jeremy Olson

TESTS	UNITS	METHODS	SPECIFICATIONS ⁽¹⁾	RESULTS
Lubricity- Fluid Temperature	°C	ASTM 6079	---	60
Major Axis	mm			0.42
Minor Axis	mm			0.37
Wear Scar Diameter	um			400

(1) Specifications not provided by the client



Iftikhar Chughtai, Laboratory Manager

The information contained herein is based on laboratory tests and observations performed by Intertek Caleb Brett. This sample (or these samples) was or were submitted by the client solely for testing. Intertek Caleb Brett disclaims any and all liability for damage or injury which results in the use of the information contained herein; and nothing contained herein shall constitute a guarantee, warranty or representation by Intertek Caleb Brett with respect to the accuracy of the information, the sample, products or items described, or their suitability for use for any specific purpose. This report is for the exclusive use of the client and may only be reproduced in full by written permission of Intertek Caleb Brett. Unless otherwise instructed, all samples pertaining to this report will be discarded 45 days after the issuing date of this report.

Intertek Caleb Brett

651 Burlington Street East, Hamilton, Ontario, Canada L8L 4J5
Telephone 905-529-0090 Fax 905-529-5989 e-mail Iftikhar.chughtai@intertek.com